

1565 West 400 North • P.O. Box 538 • Orem, UT 84059 • (801) 765-7800 • Fax (801) 765-7830 • www.genevarock.com

## AGGREGATE SUBMITTAL

## **Report of Physical Properties**

\_\_\_\_\_

GRP Material Description: 3/8" Crushed Limestone Fines

Report Date: January 4, 2024

GRP Material Code: FINE

Reviewed by: Dan McDaniel

Source Location/Code: Pelican Point / 520

Report No. 520FINE00124

-		TEST RESULTS	-		
Standard		ICAL PROPERTIES	Result	Test Source	AS
ASTM C 29	Unit	Unit Weight, lbs./cu.ft. =	111.0		Siev
AASHTO T19	Weight	Voids, % =	33		450 m
		Jig Lq ✓ Rodd			375 n
ASTM D1557	Modified	Max. density, lbs./cu.ft. =	134.4		300 m
AASHTO T180	Proctor	Optimum Moisture, % =	8.6		250 n
ASTM D698	Standard	Max. density, lbs./cu.ft. =	130.0		225 r
AASHTO T99	Proctor	Optimum Moisture, % =	11.5		200 ו
ASTM D4318	Liquid Limit	Liquid Limit=	0		150 ו
AASHTO T89/90	Plastic Limit	Plastic Limit=	0		125 ו
	Plasticity Index	Plasticity Index=	NP		100 ו
ASTM C131	L.A.	Small Coarse Loss, % =			75.0
AASHTO T96	Abrasion	Grading/Revolutions, =			63.0 m
ASTM C535	L.A.	Large Coarse Loss, % =			50.0
	Abrasion	Grading/Revolutions, =			37.5 m
	Fine	Bulk Specific Gravity (dry) =	2.628		25.0
ASTM C 128	Specific	Bulk Specific Gravity, SSD =	2.657		19.0 n
AASHTO T84	Gravity &	Apparent Specific Gravity =	2.706		12.5 n
	Absorption	Absorption, % =	1.1		9.5 m
	Coarse/Fine	Bulk Specific Gravity (dry) =			6.3 m
ASTM C 127/128	Specific	Bulk Specific Gravity, SSD =			4.75 m
AASHTO T85/84	Gravity &	Apparent Specific Gravity =			2.36 m
	Absorption	Absorption, % =			2.00 m
ASTM D2419	Sand	Sand Equivalent, % =	70		1.18 m
AASHTO T176	Equivalent				0.600 m
	Soundness	Coarse Soundness Loss, % =			0.425 m
ASTM C 88		Magnesium No. of Cycles =			0.300 m
AASHTO T104	Soundness	Fine Soundness Loss, % =	2		0.180 m
		Magnesium No. of Cycles =	5		0.150 m
ASTM C 1252	Fine Aggregate	Uncompacted Voids, % =	49		0.075 m
AASHTO T304	Angularity	Method C (as received material)			ASTM D422
ASTM C40	Organic	Coarse Aggregate, % =			
AASHTO T21	Impurities	Fine Aggregate, % =	Lighter I	Plate 1	ASTM C566
ASTM C142	Clay / Friable	Coarse Aggregate, % =			Moisture
AASHTO T112	Particles	Fine Aggregate, % =	0.4		ASTM C136 A
ASTM C123	Lightweight	Coarse Aggregate, % =			Fineness M
AASHTO T113	Pieces	Fine Aggregate, % =	0.0		AASHTO M14
ASTM D1883	CBR	Surcharge = 10 lbs CBR @ 0.1"=	85		Classifica
AASHTO T193		Swell% = 0.0% CBR @ 0.2"=	104		ASTM D479
ASTM D5821	Fractured Face	1 or 2 Faces =			Flat & E
		Fractured Face, % =			
ASTM D2487	Soil Classification	Group Symbol =			
		Group Name =			
ASTM D2488	Soil Description &	Group Symbol =			
	Identification	Group Name =			
	identification		1		

	1010					
SIEVE ANALYSIS						
	SHTO T27	-				
Sieve Size	% Passing	Spec.				
450 mm (18")						
375 mm (15")						
300 mm (12")						
250 mm (10")						
225 mm (9")						
200 mm (8")						
150 mm (6")						
125 mm (5")						
100 mm (4")						
75.0 mm (3")						
63.0 mm (2-1/2")						
50.0 mm (2")						
37.5 mm (1-1/2")						
25.0 mm (1")						
19.0 mm (3/4")						
12.5 mm (1/2")	100					
9.5 mm (3/8")	99					
6.3 mm (1/4")	91					
4.75 mm (No.4)	78					
2.36 mm (No.8)	51					
2.00 mm (No.10)	38					
1.18 mm (No.16)	34					
0.600 mm (No.30)	25					
0.425 mm (No.40)	21					
0.300 mm (No.50)	19					
0.180 mm (No.80)						
0.150 mm (No.100)	14					
0.075 mm (No.200)	10.9					
ASTM D422						
Hydrometer =						
ASTM C566 AASHTO T255						
Moisture Content, % =						
ASTM C136 AASHTO T27						
Fineness Modulus (FM) =						
AASHTO M145						
Classification of Soils =	A1A					
ASTM D4791 Ratio =						
Flat & Elongated, % =						