



AGGREGATE SUBMITTAL
Report of Physical Properties

GRP Material Description: Rock, 1 1/2"

Report Date: January 13, 2026

GRP Material Code: ROCF

Reviewed by: Dan McDaniel

Source Location/Code: North Hansen / 527(525)

Report No. 527ROCF00126

TEST RESULTS				SIEVE ANALYSIS			
Standard	PHYSICAL PROPERTIES		Result	Test Spec.	ASTM C136	AASHTO T27	
ASTM C 29 AASHTO T19	Unit Weight	Unit Weight, lbs./cu.ft. =	90		Sieve Size	% Passing	Spec.
	Weight	Voids, % =	44		450 mm (18")		
		<input type="checkbox"/> Jigged <input type="checkbox"/> Loose <input checked="" type="checkbox"/> Rodded			375 mm (15")		
ASTM D1557 AASHTO T180	Modified Proctor	Max. density, lbs./cu.ft. =			300 mm (12")		
		Optimum Moisture, % =			250 mm (10")		
ASTM D698 AASHTO T99	Standard Proctor	Max. density, lbs./cu.ft. =			225 mm (9")		
		Optimum Moisture, % =			200 mm (8")		
ASTM D4318 AASHTO T89/90	Liquid Limit Plastic Limit Plasticity Index	Liquid Limit =	0		150 mm (6")		
		Plastic Limit =	0		125 mm (5")		
		Plasticity Index =	0		100 mm (4")		
ASTM C131 AASHTO T96	L.A. Abrasion	Small Coarse Loss, % =			75.0 mm (3")		
		Grading/Revolutions, =			63.0 mm (2-1/2")		
ASTM C535	L.A. Abrasion	Large Coarse Loss, % =	22		50.0 mm (2")	100	
		Grading/Revolutions, =	3/1000		37.5 mm (1-1/2")	98	
ASTM C 128 AASHTO T84	Fine Specific Gravity & Absorption	Bulk Specific Gravity (dry) =			25.0 mm (1")	22	
		Bulk Specific Gravity, SSD =			19.0 mm (3/4")	3	
		Apparent Specific Gravity =			12.5 mm (1/2")	2	
		Absorption, % =			9.5 mm (3/8")	1	
ASTM C 127 AASHTO T85	Coarse Specific Gravity & Absorption	Bulk Specific Gravity (dry) =	2.557		6.3 mm (1/4")		
		Bulk Specific Gravity, SSD =	2.580		4.75 mm (No.4)		
		Apparent Specific Gravity =	2.618		2.36 mm (No.8)		
		Absorption, % =	0.9		2.00 mm (No.10)		
ASTM D2419 AASHTO T176	Sand Equivalent	Sand Equivalent, % =			1.18 mm (No.16)		
					0.600 mm (No.30)		
ASTM C 88 AASHTO T104	Soundness	Coarse Soundness Loss, % =	1		0.425 mm (No.40)		
		Sodium No. of Cycles =	5		0.300 mm (No.50)		
	Soundness	Fine Soundness Loss, % =			0.180 mm (No.80)		
		Sodium No. of Cycles =			0.150 mm (No.100)		
ASTM C 1252 AASHTO T304	Fine Aggregate Angularity	Uncompacted Voids, % =			0.075 mm (No.200)	0.8	
		Method C (as received material)					
ASTM C40 AASHTO T21	Organic Impurities	Coarse Aggregate, % =	0.0		ASTM D422		
		Fine Aggregate, % =			Hydrometer =		
ASTM C142 AASHTO T112	Clay / Friable Particles	Coarse Aggregate, % =	0.0		ASTM C566 AASHTO T255		
		Fine Aggregate, % =			Moisture Content, % =		
ASTM C123 AASHTO T113	Lightweight Pieces	Coarse Aggregate, % =	0.0		ASTM C136 AASHTO T27		
		Fine Aggregate, % =			Fineness Modulus (FM) =		
ASTM D1883 AASHTO T193	CBR	Surcharge = 10 lbs CBR @ 0.1" =			AASHTO M145		
		Swell% = 0.0% CBR @ 0.2" =			Classification of Soils =		
ASTM D5821	Fractured Face	1 or 2 Faces =	1=100	2=98	ASTM D4791	Ratio =	5:1
		Fractured Face, % =	3=92		Flat & Elongated, % =		0.0
AASHTO T288	Resistivity	10300chm-cm			AASHTO T267 Organic Content of Soils 0.01		
AASHTO T289 PH 8.91	AASHTO T291 Chlorides 5.08 PPM	AASHTO T290 Sulfates 5.00 PPM					