



AGGREGATE SUBMITTAL

Report of Physical Properties

GRP Material Description: Washed, Squeegy Chip

Report Date: September 9, 2026

GRP Material Code: CHPB

Reviewed by: Dan McDaniel

Source Location/Code: POM / 533

Report No. 533CHPB00426

TEST RESULTS					SIEVE ANALYSIS		
Standard	PHYSICAL PROPERTIES		Result	Test Source	ASTM C136	AASHTO T27	
ASTM C 29 AASHTO T19	Unit Weight	Unit Weight, lbs./cu.ft. =	102		Sieve Size	% Passing	Spec.
	Weight	Voids, % =	35		450 mm (18")		
		☐ Jigged ☐ Loose ☒ Rodded			375 mm (15")		
ASTM D1557 AASHTO T180	Modified Proctor	Max. density, lbs./cu.ft. =			300 mm (12")		
		Optimum Moisture, % =			250 mm (10")		
ASTM D698 AASHTO T99	Standard Proctor	Max. density, lbs./cu.ft. =			225 mm (9")		
		Optimum Moisture, % =			200 mm (8")		
ASTM D4318 AASHTO T89/90	Liquid Limit	Liquid Limit=	0		150 mm (6")		
	Plastic Limit	Plastic Limit=	0		125 mm (5")		
	Plasticity Index	Plasticity Index=	0		100 mm (4")		
ASTM C131 AASHTO T96	L.A. Abrasion	Small Coarse Loss, % =	24		75.0 mm (3")		
		Grading/Revolutions, =	D:500		63.0 mm (2-1/2")		
ASTM C535	L.A. Abrasion	Large Coarse Loss, % =			50.0 mm (2")		
		Grading/Revolutions, =			37.5 mm (1-1/2")		
ASTM C 128 AASHTO T84	Fine Specific Gravity & Absorption	Bulk Specific Gravity (dry) =			25.0 mm (1")		
		Bulk Specific Gravity, SSD =			19.0 mm (3/4")		
		Apparent Specific Gravity =			12.5 mm (1/2")		
		Absorption, % =			9.5 mm (3/8")	97	
ASTM C 127 AASHTO T85	Coarse Specific Gravity & Absorption	Bulk Specific Gravity (dry) =	2.53		6.3 mm (1/4")	94	
		Bulk Specific Gravity, SSD =	2.566		4.75 mm (No.4)	87	
		Apparent Specific Gravity =	2.625		2.36 mm (No.8)	45	
		Absorption, % =	1.4		2.00 mm (No.10)	19	
ASTM D2419 AASHTO T176	Sand Equivalent	Sand Equivalent, % =			1.18 mm (No.16)	12	
					0.600 mm (No.30)	4	
ASTM C 88 AASHTO T104	Soundness	Coarse Soundness Loss, % =	2		0.425 mm (No.40)	3	
		Magnesium No. of Cycles =	5		0.300 mm (No.50)	2	
	Soundness	Fine Soundness Loss, % =			0.180 mm (No.80)		
		Magnesium No. of Cycles =			0.150 mm (No.100)	1	
ASTM C 1252 AASHTO T304	Fine Aggregate Angularity	Uncompacted Voids, % =			0.075 mm (No.200)	0.6	
		Method C (as received material)			ASTM D422		
ASTM C40 AASHTO T21	Organic Impurities	Coarse Aggregate, % =	Lighter Plate 1		Hydrometer =		
		Fine Aggregate, % =			ASTM C566 AASHTO T255		
ASTM C142 AASHTO T112	Clay / Friable Particles	Coarse Aggregate, % =	1		Moisture Content, % =		
		Fine Aggregate, % =			ASTM C136 AASHTO T27		
ASTM C123 AASHTO T113	Lightweight Pieces	Coarse Aggregate, % =	0		Fineness Modulus (FM) =		
		Fine Aggregate, % =			AASHTO M145		
ASTM D1883 AASHTO T193	CBR	Surcharge = 10 lbs CBR @ 0.1"=			Classification of Soils =		
		Swell% = 0.0% CBR @ 0.2"=			ASTM D4791 Ratio =	5:01	
ASTM D5821	Fractured Face	1 or 2 Faces =			Flat & Elongated =	0	
		Fractured Face, % =					
ASTM D2487	Soil Classification	Group Symbol =					
		Group Name =					
ASTM D2488	Soil Description & Identification	Group Symbol =					
		Group Name =					