

1565 West 400 North • P.O. Box 538 • Orem, UT 84059 • (801) 765-7800 • Fax (801) 765-7830 • www.genevarock.com

AGGREGATE SUBMITTAL

Report of Physical Properties

GRP Material Description: Washed, Standard 3/8" x #16

Report Date: July 20, 2023

GRP Material Code: CHIP

Reviewed by: Dan McDaniel

Source Location/Code: Bauer / 560

Report No. 560CHIP00223

| TEST RESULTS | | | | | SIEVE ANALYSIS | | |
|---------------|---------------------|---------------------------------|--------|-------------|---------------------------|-----------|---|
| Standard | PHYSICAL PROPERTIES | | Result | Test Source | ASTM C136 AA | SHTO T27 | |
| ASTM C 29 | Unit | Unit Weight, lbs./cu.ft. = | 98 | | Sieve Size | % Passing | I |
| AASHTO T19 | Weight | Voids, % = | 50 | | 450 mm (18") | | |
| | | Jigged Loose Rodded | | | 375 mm (15") | | |
| ASTM D1557 | Modified | Max. density, lbs./cu.ft. = | | | 300 mm (12") | | |
| AASHTO T180 | Proctor | Optimum Moisture, % = | | | 250 mm (10") | | Ι |
| ASTM D698 | Standard | Max. density, lbs./cu.ft. = | | | 225 mm (9") | | Ι |
| AASHTO T99 | Proctor | Optimum Moisture, % = | | | 200 mm (8") | | Ι |
| ASTM D4318 | Liquid Limit | Liquid Limit= | | | 150 mm (6") | | |
| AASHTO T89/90 | Plastic Limit | Plastic Limit= | | | 125 mm (5") | | |
| | Plasticity Index | Plasticity Index= | NP | | 100 mm (4") | | Ι |
| ASTM C131 | L.A. | Small Coarse Loss, % = | 26 | | 75.0 mm (3") | | Ι |
| AASHTO T96 | Abrasion | Grading/Revolutions, = | D/500 | | 63.0 mm (2-1/2") | | I |
| ASTM C535 | L.A. | Large Coarse Loss, % = | | | 50.0 mm (2") | | Ī |
| | Abrasion | Grading/Revolutions, = | | | 37.5 mm (1-1/2") | | Ţ |
| | Fine | 0 | | | 25.0 mm (1") | | Ī |
| ASTM C 128 | Specific | Bulk Specific Gravity, SSD = | | | 19.0 mm (3/4") | | Ī |
| AASHTO T84 | Gravity & | Apparent Specific Gravity = | | | 12.5 mm (1/2") | | Î |
| | Absorption | Absorption, % = | | | 9.5 mm (3/8") | 99 | t |
| | Coarse | Bulk Specific Gravity (dry) = | 2.577 | | 6.3 mm (1/4") | | t |
| ASTM C 127 | Specific | Bulk Specific Gravity, SSD = | 2.596 | | 4.75 mm (No.4) | 54 | 1 |
| AASHTO T85 | Gravity & | Apparent Specific Gravity = | 2.626 | | 2.36 mm (No.8) | 7 | 1 |
| | Absorption | Absorption, % = | 0.700 | | 2.00 mm (No.10) | | t |
| ASTM D2419 | Sand | Sand Equivalent, % = | | | 1.18 mm (No.16) | 3 | t |
| AASHTO T176 | Equivalent | | | | 0.600 mm (No.30) | 2 | t |
| | Soundness | Coarse Soundness Loss, % = | 1 | | 0.425 mm (No.40) | | t |
| ASTM C 88 | | Magnesium No. of Cycles = | 5 | | 0.300 mm (No.50) | | 1 |
| AASHTO T104 | Soundness | Fine Soundness Loss, % = | | | 0.180 mm (No.80) | · | t |
| | | Magnesium No. of Cycles = | | | 0.150 mm (No.100) | | t |
| ASTM C 1252 | Fine Aggregate | Uncompacted Voids, % = | | | 0.075 mm (No.200) | 0.4 | t |
| AASHTO T304 | Angularity | Method C (as received material) | | | ASTM D422 | | t |
| ASTM C40 | Organic | Coarse Aggregate, % = | | | Hydrometer = | | t |
| AASHTO T21 | Impurities | Fine Aggregate, % = | | | ASTM C566 AASHTO T255 | | İ |
| ASTM C142 | Clay / Friable | Coarse Aggregate, % = | 0 | | Moisture Content, % = | · | t |
| AASHTO T112 | Particles | Fine Aggregate, % = | | | ASTM C136 AASHTO T27 | | t |
| ASTM C123 | Lightweight | Coarse Aggregate, % = | | | Fineness Modulus (FM) = | | t |
| AASHTO T113 | Pieces | Fine Aggregate, % = | | | AASHTO M145 | | t |
| ASTM D1883 | CBR | Surcharge = 10 lbs CBR @ 0.1"= | | | Classification of Soils = | | t |
| AASHTO T193 | | Swell% = 0.0% CBR @ 0.2"= | | | ASTM D4791 Ratio = | | t |
| ASTM D5821 | Fractured Face | 1 or 2 Faces = | | | Flat & Elongated = | | t |
| | | Fractured Face, % = | | | . | | Ť |
| ASTM D2487 | Soil Classification | Group Symbol = | | | | | - |
| | | Group Name = | | | | | - |
| ASTM D2488 | Soil Description & | Group Symbol = | | | | | - |
| 7.0 HVI D2400 | Identification | Group Name = | | | | | - |
| | Inentification | | | | | | _ |

Spec.