



GENEVA ROCK PRODUCTS, INC.

1565 West 400 North • P.O. Box 538 • Orem, UT 84059 • (801) 765-7800 • Fax (801) 765-7830 • www.genevarock.com

AGGREGATE SUBMITTAL Report of Physical Properties

GRP Material Description: Washed, Standard, 3/8" x #16

Report Date: January 30, 2026

GRP Material Code: CHIP

Reviewed by: Dan McDaniel

Source Location/Code: 580-South Weber/Morgan 50/50 Blend

Report No. 580CHIP00126

TEST RESULTS					SIEVE ANALYSIS		
Standard	PHYSICAL PROPERTIES		Result	Test Source	ASTM C136 AASHTO T27		
ASTM C 29 AASHTO T19	Unit Weight	Unit Weight, lbs./cu.ft. =	97		Sieve Size	% Passing	Spec.
		Voids, % = ☐ Jigge ☐ Lod ☒ Rodded	41		450 mm (18")		
ASTM D1557 AASHTO T180	Modified Proctor	Max. density, lbs./cu.ft. =			375 mm (15")		
		Optimum Moisture, % =			300 mm (12")		
ASTM D698 AASHTO T99	Standard Proctor	Max. density, lbs./cu.ft. =			250 mm (10")		
		Optimum Moisture, % =			225 mm (9")		
ASTM D4318 AASHTO T89/90	Liquid Limit Plastic Limit Plasticity Index	Liquid Limit =	0		200 mm (8")		
		Plastic Limit =	0		150 mm (6")		
		Plasticity Index =	NP		125 mm (5")		
ASTM C131 AASHTO T96	L.A. Abrasion	Small Coarse Loss, % =	29		100 mm (4")		
		Grading/Revolutions, =	D/500		75.0 mm (3")		
ASTM C535	L.A. Abrasion	Large Coarse Loss, % =			63.0 mm (2-1/2")		
		Grading/Revolutions, =			50.0 mm (2")		
ASTM C 128 AASHTO T84	Fine Specific Gravity & Absorption	Bulk Specific Gravity (dry) =			37.5 mm (1-1/2")		
		Bulk Specific Gravity, SSD =			25.0 mm (1")		
		Apparent Specific Gravity =			19.0 mm (3/4")		
		Absorption, % =			12.5 mm (1/2")	100	
ASTM C 127 AASHTO T85	Coarse Specific Gravity & Absorption	Bulk Specific Gravity (dry) =	2.609		9.5 mm (3/8")	99	
		Bulk Specific Gravity, SSD =	2.646		6.3 mm (1/4")		
		Apparent Specific Gravity =	2.710		4.75 mm (No.4)	56	
		Absorption, % =	1.4		2.36 mm (No.8)	10	
ASTM D2419 AASHTO T176	Sand Equivalent	Sand Equivalent, % =			2.00 mm (No.10)		
					1.18 mm (No.16)	3	
ASTM C 88 AASHTO T104	Soundness	Coarse Soundness Loss, % =	0.9		0.600 mm (No.30)		
		Sodium No. of Cycles =	5		0.425 mm (No.40)		
	Soundness	Fine Soundness Loss, % =			0.300 mm (No.50)	2	
		Magnesium No. of Cycles =			0.180 mm (No.80)		
ASTM C 1252 AASHTO T304	Fine Aggregate Angularity	Uncompacted Voids, % =			0.150 mm (No.100)		
		Method C (as received material)			0.075 mm (No.200)	1.2	
ASTM C40 AASHTO T21	Organic Impurities	Coarse Aggregate, % =	0.0		ASTM D422		
		Fine Aggregate, % =			Hydrometer =		
ASTM C142 AASHTO T112	Clay / Friable Particles	Coarse Aggregate, % =	0.0		ASTM C566 AASHTO T255		
		Fine Aggregate, % =			Moisture Content, % =		
ASTM C123 AASHTO T113	Lightweight Pieces	Coarse Aggregate, % =	0.0		ASTM C136 AASHTO T27		
		Fine Aggregate, % =			Fineness Modulus (FM) =		
ASTM D1883 AASHTO T193	CBR	Surcharge = 10 lbs CBR @ 0.1" =			AASHTO M145		
		Swell% = 0.0% CBR @ 0.2" =			Classification of Soils =		
ASTM D5821	Fractured Face	1 or 2 Faces =	1	2	ASTM D4791 Ratio =		
		Fractured Face, % =	98	96	Flat & Elongated =		
ASTM D2487	Soil Classification	Group Symbol =			Flakiness =	26	
		Group Name =					
ASTM D2488	Soil Description & Identification	Group Symbol =					
		Group Name =					